

# Amax Filter Bags

## Technical Data Sheet-11

Quality Code		:HPS-62.5 (FIL)OWR
Composition Web :		:Acrylic + Polyester
Scrim :		:Polyester FIL
Area Weight (g/m <sup>2</sup> ):		:625 (Min 600)
ASTM D 5729		
Thickness (mm) (+ or – 10%)		:2.4
ASTM D 5729		
Air Permeability (Ltr/dm <sup>2</sup> /min)@200pa (+ or – 20%)		:130
ASTM D 737		
Tensile Strength (kgf)		
Machine		:Min 100
Cross		:Min 100
ASTM D 5035		
Bursting Strength (kg/cm <sup>2</sup> )		:Min 30
ASTM D 3786		
Temperature Resistance		
Cont. (degree cel)		:130
Peaks (degree cel)		:140
Finish		:Singed, Calendared & OWR